











TONFORD

COLOURED BODY PORCELAIN STONEWARE

| SPECIFICATION REFERENCE E.N. 14411 . APPENDIX G. GROUP BIA. GL | | TEST METHOD | REFERENCE VALUE | DECLARED VALUE |
|---|---------------------------------|-------------|-------------------|------------------------------|
|  | Dynamic coefficient of friction | ANSI-137-1 | - | > 0,50 |
|  | Chemical resistance | ASTM-650 | - | NOT AFFECTED |
|  | Resistance to freeze | ASTM-C1026 | - | RESISTANT |
|  | Static coefficient of friction | ASTM-C1028 | >0,60 dry and wet | PEI IV - PEI III (Gun Metal) |
|  | Stain Resistance | ASTM-C1378 | - | NOT AFFECTED |
|  | Water absorption | ASTM-C373 | - | ≤ 0.5% |
|  | Breaking strength | ASTM-C648 | - | ≥ 400 |
|  | Scratch hardness | MOHS | - | ≥ 7 |